



Product Code F2405/32/1

Issue No. 1

Date: 14th November 2007

EPOXY-WBE SEALER

Epoxy-WBE Sealer is a water thinned, lead free cross-linked epoxy paint designed to give excellent adhesion and durability on various surfaces.

About The Product

Water Based 2 Pack Epoxy Sealer
Industrial areas low odour
Mixing ratio 1;3 A:B by volume
Pot Life 1.5 hours
Tintable

Surfaces

- Pavements
- Concrete Floors
- Asphalt surfaces
- Brickwork

Colour: Clear

Gloss: Full

Toxicity : Lead free, non toxic when dry.

Drying Time:

- 16 hrs
- Recoat with itself 4 hours
-

Volume Solids: 23%

Weight Solids: 25%

Coverage:

Approximately 12 m² per litre, depending on the surface profile and application technique.

Mixing Instructions:

Mix components A and B thoroughly before combining.

Combine components A and B in the ratio of 1 volume of A to 3 volumes of B.

Mix thoroughly using a broad flat paddle in a scooping motion.

Alternatively use a mechanical stirrer.

Thinning: In hot conditions thin with up to 50 mls of water per litre if necessary.

Surface Preparation

Caution: Some substrates may contain asbestos. Do not carry out any work without firstly obtaining advice from your local council
Always wear a dust mask when sanding.

Previously Painted Surfaces

- Remove all dirt, grease and loose or flaking material
- Treat affected surfaces to remove mould, efflorescence or other defects.
- Fill holes and cracks with a suitable filler.
- Sand lightly and dust clean

New Surfaces

- All surfaces must be clean and dry
- Concrete and cement surfaces must be cured for at least 1 month.
- Smooth concrete surfaces should be acid etched to promote good adhesion.

Application:

- Apply by roller or brush.

Do not apply if temperature is below 10C or likely to fall below 10C during drying.

Epoxy-WBE Sealer has good resistance to splashes and spills of chemicals and solvents.

Additional:

Stepongrip anti slip grit may be added to this product for improved grip of foot traffic to W rating as per **AS/NZS 4586 - 2004**.

May be added to Transpave for additional strength:-

Mixing Ratio: 4 Litres of Epoxy-WBE mixed with 450ml water added to 15 Litres Transpave or part thereof. Note the pot life of the material will be as per Epoxy-WBE

Clean Up: Soap and water.

Flammability: Non flammable

Safety and Environment

- Keep out of the reach of children
- Ensure adequate ventilation during use and drying
- Refer Material Safety Data Sheet for full information
- Do not pour paint products down sewers or stormwater drains
- Dispose of unused paint and containers through special collection services
- Contact your local council for information about disposal

First Aid

If swallowed:

- Do not induce vomiting
- Drink plenty of water
- Seek medical advice

If in eyes:

- Flood eyes with water for 15 minutes.
- If irritation persists seek medical attention

To obtain a Material Safety Data Sheet contact:-

Ultra V Group Pty Ltd

Tel: 03 98748913

Fax: 03 98748914

Mobile: 0408288601

Email: info@ultravgroup.com.au

Disclaimer: The information in this data sheet is believed to be as up to date as possible. No responsibility is accepted or warranty given or implied since the application procedures are outside the control of the company.