



STEPETHANE30 SEALER

Product Code F2405/27/3 and F2405/27/2

Issue No. 1

Date: 14th November 2007

Stepethane30 sealer is a 2 pack acrylate polyisocyanate which provides excellent adhesion to a wide range of materials.

About The Product:

- 2 Pack
- Suitable for industrial areas
- Pot Life 24 hours
- Tintable

Surfaces:

- Pavements
- Concrete Floors
- Asphalt surfaces
- Brickwork
- Timber & Composite timber
- Epoxy

Colour: Clear

Gloss: Full

Toxicity : Lead free, non toxic when dry.

Drying Time:

- 1 hour tack free
- Recoat with itself 4 hours subject to temperature & humidity

Volume Solids: 28.5%

Weight Solids: 31%

Container Volume: 10 Litres

Coverage:

Approximately 12m² to 15m² per litre product application rate, depending on the surface profile and application technique.

Mixing Instructions:

Mix components A and B thoroughly before combining.

Combine components A and B in the ratio of 12 volume of **A** to 1 volumes of **B**. Mix thoroughly using a broad flat paddle in a scooping motion. Alternatively use a mechanical stirrer.

UV Protection:

State of the art UV absorbers are incorporated to assist in surface protection from the effects of sunlight & is resistant to yellowing and age crazing.

Surface Preparation:

Caution: Some substrates may contain asbestos. Do not carry out any work without firstly obtaining advice from your local council
Always wear a dust mask when sanding.

Previously Painted Surfaces:

- Remove all dirt, grease and loose or flaking material
- Treat affected surfaces to remove mould, efflorescence or other defects.
- Fill holes and cracks with a suitable filler.
- Sand lightly and dust clean

New Surfaces:

- All surfaces must be clean and dry
- Concrete and cement surfaces must be cured for at least 1 month.
- Smooth concrete surfaces should be acid etched to promote good adhesion.

Application:

Apply by roller or brush.

Additional:

Stepongrit anti slip grit may be added to this product for improved grip of foot traffic to W rating for wet surfaces as per **AS/NZS 4586 – 2004**

A matting agent may be added to this product to remove the **gloss** finish.

Clean Up: Xylene thinners.

Flammability: Highly Flammable.

Chemical Resistance:

Transathane Sealer has good resistance to splashes and spills of chemicals and solvents.

Safety and Environment:

- Keep out of the reach of children
- Ensure adequate ventilation during use and drying
- Refer Material Safety Data Sheet for full information
- Do not pour paint products down sewers or stormwater drains
- Dispose of unused paint and containers through special collection services
- Contact your local council for information about disposal

First Aid

If swallowed :

- Do not induce vomiting
- Drink plenty of water
- Seek medical advice

If in eyes:

- Flood eyes with water for 15 minutes.
- If irritation persists seek medical attention

To obtain a Material Safety Data Sheet contact:-

Ultra V Group Pty Ltd

Tel: 03 98748913

Fax:03 98748914

Email: info@ultravgroup.com.au

Disclaimer: The information in this data sheet is believed to be as up to date as possible. No responsibility is accepted or warranty given or implied since the application procedures are outside the control of the company.